



TRANSPARENT POLYURETHANE MEMBRANE

DESMOPOL T is a one component high solid, polyurethane resin, which once made forms a continuous, elastic, without any joints or overlapping, and totally waterproof.

It is applied manually, using a roller or brush and, exceptionally, using specific spray equipment.

USES

- Waterproofing and coating of: roofs, terraces, balconies and overhangs.

Yield	± 1 kg/m ² (1 mm thickness)
Tack free at 23 °C	± 6 hours
Elongation at 23°C	>100%
Tensile strength at 23°C	>2MPa
Dilution	5% Desmosolvent ("airless" equipment)
Application method	By brush, roll, or "airless" equipment



COLORS

Clear

GENERAL FEATURES

- DESMOPOL T is a highly elastic and wear-resistant membrane that, once applied, offers great stability and durability.
- DESMOPOL T adapts to any surface, making it the ideal product for application on uneven surfaces and in areas of any shape, whether curved or squared.
- Applying DESMOPOL T saves in seals and any other kind of joins, as the finish is uniform and makes up a single layer, providing a surface with optimum maintenance and cleaning properties.
- DESMOPOL T transparent polyurethane membrane should be applied in dry conditions avoiding the presence of humidity or water coming from the surface to be coated or the substrate, whether at the time of application or subsequently (pressure from phreatic water level).
- DESMOPOL T system doesn't require solar radiation protection (UV rays) to ensure its properties, because it is an aliphatic membrane.
- DESMOPOL T system's properties enable it to bond several kind of surfaces such as natural stone, ceramic. For other kind of supports, please, contact with TECNOPOL SISTEMAS S.L. technical department.
- High resistance all over the time, retaining its transparency.
- Use PRIMER T primer before application of membrane.
- Not recommended to use in pools, or chemically treated water, in general not use on total water immersion.
- Once formed, don't clean with bleach or highly corrosive products.
- Do not apply DESMOPOL T media with temperatures above +35 ° C
- If there is humidity or moisture in the substrate at the time of application, check the technical specifications of our primers where the maximum support humidity ranges are specified.

YIELD

Product yield is 0.5 to 1 kg/sqm, applied in 2 layers, depending on the application method and conditions.

PACKAGING

Metal tins of 20 kg and 5 kg

COLOURS

Transparent.

SHELF LIVE

12 months at temperatures between 5° C and 25° C, provided it is stored in a dry place. Once the tin has been opened, the product must be used immediately.



APPLICATION

In general, the following aspects should be dealt with prior to application:

- Support will be strong and dry.
- Clean up the surface, removing dust, oils and grasses, and existing chippings.
- We recommend applying on the substrate with the primer PRIMER T with a clean cloth and allow drying (15 - 20min).
- Can be applied by roller, brush or "airless" spray.

HANDLING

These safety recommendations for handling are necessary for the implementation process as well as in the pre-and post, on exposure to the loading machinery.

- Respiratory Protection: When handling or spraying use an air-purifying respirator.
- Skin protection: Use rubber gloves, remove immediately after contamination. Wear clean body-covering. Wash thoroughly with soap and water after work and before eating, drinking or smoking.
- Eye / Face: Wear safety goggles to prevent splashing and exposure to particles in air.
- Waste: Waste generation should be avoided or minimized. Incinerate under controlled conditions in accordance with local laws and national regulations.

Anyway, consult the material and safety data sheet (MSDS) of the product.

TECHNICAL DATA

Concepts	Results
Viscosity at 23°C	±250 cps
Specific weight at 23°C	1g/cm³
Flasch point	742 °C
Repainted time (time within layers) at 23°C	6~24 hour
Tack free at 23 °C and 55% relative humidity	±6 hours
Dry extract	±80%
Work temperature	-40at 80 °C
Surface temperature range	3~35 °C
Hardness at 23°C	ShoreA 780
Tensile strength at 23 °C	>2 MPa
Elongation at 23 °C	>100%
Potassium hydroxide contact 8% 10days at 50 °C	Nosignificant changes in the elastomeric properties
Sodium hypochlorite contact 5% 10days	Nosignificant changes in the elastomeric properties
Thermal stability (100 days at80 °C)	OK



Water absorption

< 1,4%

QUV Resistance to weather test(4hr UV, at 60 °C (UVB light) &
4hr at 50 °C)

OK3000h





PRIMER T - ONE COMPONENT, IMPREGNATION ALCOHOLIC SOLUTION CONTAINING ADHESION PROMOTERS.

Is an alcohol-based impregnation, colorless, without yellowing. Specially designed to increase adhesion on non-porous substrates, for uses under DESMOPOL T, transparent and aliphatic polyurethane membrane.

USES

- specially designed to increase adhesion of transparent and aliphatic polyurethane membrane DESMOPOL T.
- to apply on non-porous substrates such as vitrified tiles, ceramic, marble ...
- on other supports than those specified, please make a test or consult our technical department.

NOTE: call our technical department about the application to other supports or situations

dry time at 23°C	10~15 minutes
application method	use a wet rag
specific weight at 23°C	0,83 g/cm³
viscosity at 23°C	40 cps
VOC(volatile organic compounds)	823,1 g/l
flashpoint	42°C



COLORS

Transparent

GENERAL FEATURES



- Apply in thin layers using a wet rag. Approx. consumption 60 g/m²
- No dilution with any kind of solvent.
- In different supports, specified, do a previous test.
- It requires smooth, clean and dry surface without residual moisture
- Drying time: 10-15 minutes, before applying the membrane aliphatic and transparent DESMOPOL T.
- Do not apply on substrates with existing moisture/ humidity or contact with water from the inside of the support (possible phreatic water, condensation, leaks ...).

PACKAGING

Metal tins of 4 kg.



SHELF LIFE

12 months for each product at temperatures between 5° C and 35° C, provided it is stored in a dry place. Once the tin has been opened, the product must be used immediately.

HANDLING AND TRANSPORT

These safety recommendations for handling, are necessary for the implementation process as well as in the pre and post, on exposure to the loading machinery.

- Respiratory Protection: When handling or spraying use an air-purifying respirator.
- Skin protection: Use rubber gloves, remove immediately after contamination. Wear clean body-covering. Wash thoroughly with soap and water after work and before eating, drinking or smoking.
- Eye / Face: Wear safety goggles to prevent splashing and exposure to particles in the air.
- Waste: Waste generation should be avoided or minimized. Incinerate under controlled conditions in accordance with local laws and national regulations.

Anyway, consult the material and safety data sheet of the product(MSDS) or contact our technical department.

The information herein is to assist customers in determining whether our products are suitable for their applications. Our products are only intended for sale to industrial and commercial customers. Customer assumes full responsibility for quality control, testing and determination of suitability of products for its intended application or use.

We warrant that our products will meet our written liquid component specifications. We make no other warranty of any kind, either express or implied, by fact or law, including any warranty of merchantability or fitness for a particular purpose. Our total liability and customers' exclusive remedy for all proven claims is replacement of nonconforming product and in no event shall we be liable for any other damages. While descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, they are provided for guidance only. Because many factors may affect processing or application/ use, Tecnopoli Sistemas S.L recommends that the reader make tests to determine the suitability of a product for a particular purpose prior to use.

No warranties of any kind, either expressed or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding products described or designs, data or information set forth, or that the products, designs, data or information may be used without infringing the intellectual property rights of others. In no case shall the descriptions, information, data or designs provided be considered a part of Tecnopoli Sistemas S.L terms and conditions of sale. Further the descriptions, designs, data, and information furnished by Tecnopoli Sistemas S.L hereunder are given gratis and Tecnopoli Sistemas S.L assumes no obligation or liability for the description, designs, data or information given or results obtained, all such being given and accepted at the reader's risk.

All data furnished refers to standard production using manufacturing testing tolerances. The product user, and not Tecnopoli Sistemas S.L, is responsible for determining the suitability and compatibility of our products for the user's intended use.

Liability of Tecnopoli Sistemas and its affiliates for all claims is limited to the purchase price of the material.

Products may be toxic and require special precautions in handling. User should obtain detailed information on toxicity, together with proper shipping, handling and storage procedures, and comply with all applicable safety and environmental standards.

No freedom from any patents or other industrial or intellectual property rights is granted or to be inferred.

